

# Valutek Pigment Free Nitrile 12" Glove



**VTGNPFBTIO2F12** Valutek's 12-inch ambidextrous nitrile powder-free bagged glove is constructed from 100% clean, synthetic nitrile polymer containing no rubber latex with a unique pigment free formulation.

In order to develop the most chemically pure nitrile material, Valutek has removed all color pigment—the source of a known contaminant, Titanium Dioxide (TiO<sub>2</sub>)—from this specific formulation.

The result is a cleaner, translucent glove with enhanced performance and operator comfort.

## Features

- "Accelerator Free" which eliminates known allergens
- "Filler Free" which enhances ESD properties tensile and strength
- "Pigment Free" with no TiO<sub>2</sub> hard particles

Part Number: VTGNPFBTIO2F12

## Application

In addition to the standard textured fingertip and beaded long cuff design, the **"zero additive"** formulation offers the ultimate in user comfort; it is Valutek's softest, most flexible, and **"tackiest"** glove material that makes it suitable for both wet and dry applications.

Unlike most traditional clean nitrile gloves that are stiff with a slick finish, this next-generation glove is both clean yet extremely soft and operator friendly—reducing hand fatigue and increasing dexterity in a way unmatched by most **"clean"** nitrile gloves

Now that modern detection methods—Scanning Electron Microscopy—identify titanium dioxide as a source of defects and reduced yield in certain semiconductor, advanced microelectronic, and nanofabrication environments, this glove is explicitly engineered to meet these needs without jeopardizing operator dexterity and comfort.

As part of the Valutek **Microtek** product family, this cleanroom packaged glove is recommended for use in a cleanroom **Class 100-1,000 (ISO 5-6)** critical environment.

All Valutek gloves are tested and manufactured in ISO-compliant facilities under Valutek inspection and strict process control to ensure Valutek quality standards and product specifications.

## Packaging



- The outer bag contains an inner bag with 2 stacks of 50 gloves.
- Gloves packaged cuffs on the bottom, vacuum sealed, flat packed, and with a carton liner.
- 100 ea/bag, 10 bags/case, 1000 ea/case.
- Critical environment compatible.
- All gloves are **lot traceable** with retention samples held in **Quality Control for 36 months** from the date of manufacturing.



Gloves



Wipers



Apparel



Adhesive Mats



Cleaning & Maintenance



Documentation



Glove Liners



ESD



## Valutek Titanium Dioxide Free Nitrile Clenroom 12" Glove

Part Number: VTGNPFBTIO2F12

## VTGNPFBTIO2F12 Physical Properties

Part Number	Size	Palm Width (mm)	Weight (gm)	Length (inch/mm)	Test Method
VTGNPFBTIO2F12-XS	XS	75 ± 5	5.5 ± 0.2		
VTGNPFBTIO2F12-SM	SM	85 ± 5	6.0 ± 0.2		IEST-RP-CC005.4
VTGNPFBTIO2F12-MD	MD	95 ± 5	6.5 ± 0.2	12"/290	ASTM D3767
VTGNPFBTIO2F12-LG	LG	105 ± 5	7.0 ± 0.2		
VTGNPFBTIO2F12-XL	XL	115 ± 5	7.5 ± 0.2		
VTGNPFBTIO2F12-2X	2X	125 ± 5	8.0 ± 0.2		

Tensile Properties	Tensile Strength	Ultimate Elongation	Test Method	Measured Points	Thickness	Test Method	Surface Texture	Friction	Test Method
Before Aging	18 MPa, min	500%, min	ASTM D412	Fingertip	4.72 mil 0.12 mm, min	ASTM D3767	Tackiness	< 200 gmf	ASTM D1894
After Aging	16 MPa, min	450%, min		Palm	3.94 mil 0.10 mm, min				
				Cuff	3.15 mil 0.08 mm, min				

\*Barrier Integrity: AQL 1.5

## VTGNPFBTIO2F12 Technical Performance

Attribute	Value	Units	Test Method
<b>Particle Counts</b>			
LPC: ≥0.5 μm	<2,000	particles/cm <sup>2</sup>	IEST-RP-CC005.4, Sec 16.4
<b>SEM-EDX</b>			
Titanium Dioxide (TiO <sub>2</sub> )	Absent		SEM-EDX - Stamping method
<b>Non Volatile Residue (NVR)</b>			
DI Water	<2.0	μg/cm <sup>2</sup>	IEST-RP-CC005.4, Sec 17.2
IPA	<5.0	μg/cm <sup>2</sup>	IEST-RP-CC005.4, Sec 17.2
<b>FTIR</b>			
Silicone Oil, Amide, DOP	Not Detectable		IEST-RP-CC005.4, Sec 17.4

Extractable Counts (Ions)					
Sodium(Na)	<0.02	μg/cm <sup>2</sup>	Fluoride(F <sup>-</sup> )	<0.001	μg/cm <sup>2</sup>
Potassium(K)	<0.02	μg/cm <sup>2</sup>	Bromide(Br <sup>-</sup> )	<0.001	μg/cm <sup>2</sup>
Calcium(Ca)	<0.50	μg/cm <sup>2</sup>	Phosphate(PO <sub>4</sub> <sup>3-</sup> )	<0.002	μg/cm <sup>2</sup>
Magnesium(Mg)	<0.005	μg/cm <sup>2</sup>	Chloride(Cl <sup>-</sup> )	<0.60	μg/cm <sup>2</sup>
Ammonium(NH <sub>4</sub> <sup>+</sup> )	<0.005	μg/cm <sup>2</sup>	Sulfate(SO <sub>4</sub> <sup>2-</sup> )	<0.20	μg/cm <sup>2</sup>
Nitrate(NO <sub>3</sub> <sup>-</sup> )	<0.50	μg/cm <sup>2</sup>	Nitrite(NO <sub>2</sub> <sup>-</sup> )	<0.001	μg/cm <sup>2</sup>
Lithium(Li)	<0.005	μg/cm <sup>2</sup>	Aluminium(Al)	<0.01	μg/cm <sup>2</sup>
Zinc(Zn)	<0.10	μg/cm <sup>2</sup>	Iron(Fe)	<0.005	μg/cm <sup>2</sup>
Copper(Cu)	<0.0004	μg/cm <sup>2</sup>			

## ESD Properties

Electrostatic Decay	<5 seconds	Tribo Charge	<50 V	ANSI/ESD SPI5.1
Surface Resistivity	<1 X 10E11 Ω			

\*Note: Technical data listed reflects upper/lower limits. Certificates of Analysis available upon request for actual lot-to-lot test data. 36 month lot trend analysis available upon request



Valutek WEST  
Phoenix, AZ - USA

Valutek EAST  
Albany, NY - USA

Valutek ASIA  
Penang - Malaysia

1.800.763.1250

orderdesk@valutek.com

valutek.com

INNOVATIVE SOLUTIONS FOR CRITICAL ENVIRONMENTS