Valutek Ultra Thin Powder Free 12" Nitrile Glove





Valutek's ultra thin 12"ambidextrous powder-free cleanroom nitrile glove is constructed from 100% clean synthetic nitrile polymer and contains no rubber latex.

This glove has a textured fingertip and a beaded long cuff design which offers the ultimate cleanliness and operator dexterity with very low levels of particle and extractable counts.

All Valutek gloves are tested and manufactured in ISO-compliant facilities, to subject Valutek inspection and stringent process control, ensuring compliance with Valutek quality standards and product specifications.

Part Number: VTGNUTCRB12

Packaging

- 100% clean and synthetic nitrile polymer (Acrylonitrile Butadiene)
- Accelerator and sulfur free
- 12"/290 mm length with beaded long cuff
- Textured fingertips
- Powder-free, double chlorination and 18 mega-ohm D.I. water rinse
- Low levels of particles and extractable counts
- ESD-compliant, acid and solvent-compatible

Application

As part of the Valutek Nanotek product line, this glove is packaged for cleanrooms and recommended for use in a Class 1-10 (ISO 3-4) critical environment.

It is recommended for a wide variety of applications requiring exceptionally clean gloves, such as wafer fabrication, disk drive assembly, semiconductor manufacturing, biotechnology, nonaseptic pharmaceutical production, and optics.

Packaging





- The Outer bag contains inner bag with 2 stacks of 50 gloves.
- Gloves packaged cuffs on bottom, vacuum sealed, flat packed and with a carton liner.
- 100 ea/bag, 10 bags/case, 1000 ea/case.
- Critical environment compatible.
- All gloves are lot trace-able with retention samples held in Quality Control for 36 months from the date of manufacturing.

















www.valutek.com

Valutek Ultra Thin Powder Free 12" Nitrile Glove Part Number: VTGNUTCRB12



VTGNUTCRB12 Physical Properties

Part Number	Size	Palm Width (mm)	Weight (gm)	Length (inch/mm)	Test Method
VTGNUTCRB12-XS	XS	70 ± 10	3.5 ± 0.2		
VTGNUTCRB12-SM	SM	80 ± 10	4.0 ± 0.2		IEST-RP-CC005.4
VTGNUTCRB12-MD	MD	95 ± 10	4.5 ± 0.2	12"/290 mm	ASTM D6319
VTGNUTCRB12-LG	LG	110 ± 10	5.0 ± 0.2		
VTGNUTCRB12-XL	XL	120± 10	5.6 ± 0.2		
Tanaila - "					

Tensile Properties	Tensile Strength	Ultimate Elongation	Test Method
Before Aging	14 MPa, min	500%, min	
After Aging	14 MPa, min	400%, min	ASTM D6319
3 3	1 1 Wii G, 11 III 1	10070, 111111	

^{*}Barrier Integrity: AQL 1.5

VTGNUTCRB12 Technical Performance

Attribute	Value	Units	Test Method
Particle Counts			
LPC: ≥0.5 μm	<800	particles/cm ²	IEST-RP-CC005.4, Sec 16.4
Non Volatile Residue (NVR)			
Total NVR	<30	mg/g	IEST-RP-CC005.4, Sec 17.2
FTIR			
Silicone Oil, Amide, DOP	Not Detectable		IEST-RP-CC005.4, Sec 17.4
Extractable Counts (lons)			
Sodium(Na) Potassium(K) Calcium(Ca) Magnesium(Mg) Ammonium(NH4 ⁺)	<0.050 mg/g <0.050 mg/g <0.200 mg/g <0.010 mg/g <0.050 mg/g	Fluoride(F-) <0.001 mg/g Bromide(Br ⁻) <0.001 mg/g Phosphate(PO4 ³⁻) <0.001 mg/g Chloride(Cl ⁻) <0.100 mg/g Sulfate(SO4 ²⁻) <0.050 mg/g	IEST-RP-CC005.4, Sec 17
Nitrate(NO3-) Lithium(Li)	<0.050 mg/g <0.001 mg/g	Nitrite(NO ₂ ⁻) <0.001 mg/g	

ESD Properties				
Electrostatic Decay	<3 seconds	Tribo Charge	<150 V	ANSI/ESD SP15.1
Surface Resistivity	10 ⁹ - 10 ¹¹ ohm/sq			

*Note: Technical data listed reflects upper/lower limits. Certificates of Analysis available upon request for actual lot-to-lot test data.

36 month lot trend analysis available upon request



Valutek WEST Phoenix, AZ - USA ✓ Valutek EAST

Penang - Malaysia

1.800.763.1250

orderdesk@valutek.com